



October 24, 2018

Mr. Jeffrey West
Allied Industries International Inc.
3013 Bank Street
Charlotte, NC 28203

Dear Mr. West:

On behalf of the National Floor Safety Institute, I would like to thank you for submitting your product for Phase 1 testing. The product listed below was tested per the ANSI/NFSI B101.1-2009 Test Method for Measuring Wet SCOF of Common Hard-Surface Floor Materials and the ANSI/NFSI B101.3-2012 Test Method for Measuring Wet DCOF of Common Hard-Surface Floor Materials on October 24, 2018.

Product	Average SCOF	Pass/Fail	Average DCOF	Pass/Fail
Eco-Grip Sample 1	.62 0.62	Pass	.43 0.55	Pass
Eco-Grip Sample 2	0.72	Pass	0.57	Pass

The product meets our minimum acceptable wet SCOF value of 0.60 and our minimum wet DCOF value of 0.42, therefore the product is eligible for Phase 2 testing. Again, thank you for submitting your product to the NFSI.

Sincerely,

A handwritten signature in blue ink, appearing to read "Russell J. Kendzior", is written over a horizontal line.

Russell J. Kendzior
President